

**STARKEM s.r.l.**

società con socio unico soggetta a direzione e coordinamento di Quadragono S.r.l.  
Via Donatori di Sangue, 32 – 31029 Vittorio Veneto (TV) ITALY  
Tel. +39 0438 912693 Fax +39 0438 912175  
Codice Fiscale / Iscr. Reg. Imprese TV 03491050260  
Partita IVA: IT03491050260  
Cap. Soc. € 50.000,00 I.V.  
info@starkem.com - www.starkem.com



---

## SPECIFICATION FOR THE APPLICATION OF FIREBLOCK® 1001/EU

Painting of (1)\_\_\_\_\_

The treatment will be made by (2)\_\_\_\_\_ application of  
fire retardant paint called FIREBLOCK® 1001/EU.

The application cycle provides the following procedures:

### 1) PREPARATION OF THE SURFACES

Verify that the materials to protect are free of grease, fats, oil, waxy impregnating and preexisting varnishes. Existing paint coats must be removed by sandblasting or by sandpapering with coarse grain and then fine abrasive paper at naked wood.

After this operation, in order to ensure maximum adherence of fire retardant paint on the support, carry out further cleaning using a dampened cloth with nitro thinner to remove completely from wood traces of wax.

It should be checked carefully that the humidity of the wooden materials to coated is less than the value of 12% in weight.

If the conditions of preparation above indicated are not respected, we don't give any guarantee of durability of treatment.

### 2) WATER BASED IMPREGNATING AGENT FOR WOOD

Application of our product STARWOOD/W, water based primer, in amount of 80-100 g/m<sup>2</sup> in order to confer resistance to mold and pests of wood (this treatment should be done on naked wood). The product is supplied in transparent or colored version.

### 3) FIRE RETARDANT PAINT

Application of two coats of paint FIREBLOCK® 1001/EU with a consumption of 200 g/m<sup>2</sup> each, after drying the first coat, if the product is applied by roller or brush; apply one coat of paint FIREBLOCK® 1001/EU with a consumption of 400 g/m<sup>2</sup>, if the product is applied by spray (airless device without filter with nozzle 31).

Drying time between the two coats: 10 hours at +20°C. The total quantity of paint applied, therefore, amounts to 400 g/m<sup>2</sup>.

For any information not mentioned above, please look at our technical data sheets.

- 
- 1) Indicate the type of wood support to treat (wall, matchboard, false ceiling, etc.) and the quality of the wood used (fir, beech, oak, etc.)
  - 2) Indicate the application system used (spray, brush, roller, etc.)
-